



Selectarc Cu116

Basic coated Cu-Al
Bronze Electrode

Classification

AWS A5.6 : ~ECuAl-A2 DIN 1733 : EL-CuAl9
ISO 1777 : E Cu 6100A (CuAl9)

Description & Applications

Basic coated electrode for joining and surfacing on aluminium bronzes with up to 10%Al and for dissimilar joints between steels and CuAl-bronzes. Also recommended for overlays on cast iron, steels and copper alloys. Excellent weldability, stable arc, less spatters, easy to remove slag.

Main applications: Ship building, sea water applications, desalination plants, chemical industry, pump parts which are attacked by salt water (propellers, bearings...).

Base materials

UNS	Alloy	DIN	Material N°
C60600		CuAl5	2.0916
C61000		CuAl8	2.0920
C68700	Yorcalbro	CuZn20Al2	2.0460

Typical Weld Metal Composition (%)

Al	Mn	Fe	Cu
8.0	1.0	0.7	Rem.

All Weld Metal Mechanical Properties


R _{p0.2} (MPa)	R _m (MPa)	A ₅ (%)	Hardness
180	420	>20	180 HB

Welding Current & Instructions

Electrode	ØxL (mm)	2,5x350	3,2x350	4,0x350
Current	(A)	80-100	90-120	120-140

Redrying 2 h at 250°C. Joints to weld must be clean, exempt from grease, cracks. Guide electrodes with a slight declination (10-20°) inclined in direction of travel). Weld with a short arc. To improve degassing of the deposit, adopt a low welding speed. Heavy pieces (sections above 6 mm) have to be preheated to 150-250°C.

ind.12



Liability: This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.